

AA
situated near the bottom of the spinning vat (12) in order to guide the film tube (10) around and, afterwards, out of the spinning vat (12) in an upward sloping manner.

The film tube is laid flat along a contact section (27) of the idle roller (13).

REMARKS

Applicants respectfully request that the foregoing amendments be made prior to examination of the present application.

Respectfully submitted,

June 15, 2001
Date

Susan E. Shaw McBee
Susan E. Shaw McBee
Reg. No. 39,294

HELLER EHRMAN WHITE & McAULIFFE LLP
1666 K Street, N.W.
Suite 300
Washington, D.C. 20006
Tel: 202-912-2000
Fax: 202-912-2020



26633

PATENT TRADEMARK OFFICE

JUN 15 2001

PATENT AND TRADEMARK OFFICE

MARKED-UP COPY OF AMENDED ABSTRACT

The invention relates to a film tube (10) based on cellulose which is produced by extruding an aqueous cellulose-N-methyl-morpholine-N-oxide (NMMO) solution through a ring nozzle (21) onto a lining (3). The film tube (10) is manufactured by means of a vertically descending spinning in a spinning vat (12) in which a spinning bath (11) is located. The film tube (10) which is submerged in the spinning bath (11) passes through an air gap (9) between the underside of a nozzle block (7) and the upper surface of the spinning bath (11) and, internally, is pressurized, supported and slightly [strctechd] stretched in a transversal manner by compressed air. The film tube (10) is filled with an inner bath solution (31) via a supply tube (18). An idle roller (13) is situated near the bottom of the spinning vat (12) in order to guide the film tube (10) around and, afterwards, out of the spinning vat (12) in an upward sloping manner. The film tube is laid flat along a contact section (27) of the idle roller (13).

09787416-061501